

## TEST REPORT

DATE: 10-31-2024

Page 1 of 1

TEST NUMBER: 0311620

<b>CLIENT</b>	Palziv North America
<b>TEST METHOD CONDUCTED</b>	AATCC 205 Carpet: Liquid Penetration by Spillage
<b>DESCRIPTION OF TEST SAMPLE</b>	
<b>IDENTIFICATION</b>	HQ .1875" Commercial Cushion
<b>REFERENCE</b>	PO24001640

### CONCEPT

This test method is used for purposes of determining the impermeability of floor covering materials to aqueous solutions.


### PROCEDURE

One hundred ml of methylene blue dye was poured through a funnel with a 10 mm diameter spout from a height of one meter onto the surface of a clean floor covering sample in a concentrated area. After a 24 hour conditioning time of 20° C and 65% relative humidity, a visual examination was performed on five cross-sections from spill area to determine the transfer of the dye into the backing.

### TEST RESULTS

<b>RESULTS</b>	PASSES: No Penetration Occurred
----------------	---------------------------------

APPROVED BY:



This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.