

TEST REPORT

DATE: 10-31-2024

Page 1 of 1

TEST NUMBER: 0311620

CLIENT	Palziv North America
---------------	----------------------

TEST METHOD CONDUCTED	ASTM D3574 Foam Summary
------------------------------	-------------------------

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	HQ .1875" Commercial Cushion
REFERENCE	PO24001640


GENERAL PRINCIPLE

The samples were prepared and tested in accordance with applicable portions of test method ASTM D3574.

TEST RESULTS

TEST DESCRIPTION	METHOD	RESULTS
Compression Set @ 50%	ASTM D3574	7.4%
Compression Resistance Str @ 10%	ASTM D3574	5.0 psi
Compression Resistance Str @ 25%	ASTM D3574	8.7 psi
Compression Resistance Str @ 50%	ASTM D3574	18.9 psi
Compression Resistance Str @ 60%	ASTM D3574	26.8 psi
Compression Resistance Str @ 70%	ASTM D3574	40.5 psi
Compression Resistance Str @ 80%	ASTM D3574	69.1 psi
Indentation Force Deflection @ 25%	ASTM D3574	534.8 lbs.
Indentation Force Deflection @ 65%	ASTM D3574	1,985.4 lbs.
CDF @ 25%	ASTM D3574	6.6 lbs.
CDF @ 65%	ASTM D3574	31.3 lbs.

APPROVED BY:



This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products.

This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.